END

FILMED

DTIC

MICROCOPY RESOLUTION TEST CHART

NATIONAL BUREAU OF STANDARDS-1963-A

AD-A151 446

DTIC FILE COPY

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 6	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A Soluble Linear Schiff-Base Coordination Polymer Containing Eight-Coordinate Zirconium(IV)		5. TYPE OF REPORT & PERIOD COVERED Technical Report, Interim
		6. PERFORMING ORG. REPORT NUMBER
AUTHOR(s) Ronald D. Archer, Marvin L. Illingsworth, Denise N. Rau and Christopher J. Hardiman		8. CONTRACT OR GRANT NUMBER(s) N00014-81-K0611
PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry University of Massachusetts Amherst, MA 01003		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR056-773
CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, VA 22217		12. REPORT DATE February, 1985
		13. NUMBER OF PAGES 31
14. MONITORING AGENCY NAME & ADDRESS(if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

Approved for Public Release, Distribution Unlimited

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

This document has been approved for public release and sale; its distribution is unlimited

18. SUPPLEMENTARY NOTES

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

bridging ligands
coordination polymer
eight-coordinate chelate polymer
film-forming metal chelate polymer
gel permeation chromatography

Schiff-base coordination polymer
thermal stability
zirconium polymer

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

The first soluble linear Schiff-base heavy metal coordination polymer has been synthesized via the condensation of 1,2,4,5-tetraaminobenzene and tetrakis-(salicylaldehydato)zirconium(IV) in dry dimethyl sulfoxide. The N,N',N'',N'''-tetrasalicylidene-1,2,4,5-tetraaminobenzeneatozirconium(IV) polymer has a number average molecular weight of up to 4.9×10^4 based on inherent viscosity, gel permeation chromatography, and elemental analysis. Spectral properties of this polymer indicate a structure analogous to the model compound, bis(N,N'-disalicylidene-1,2-phenylenediamino)zirconium(IV). Thermal characterization of ---

DD FORM 1473
1 JAN 73

85 03 06 005

OFFICE OF NAVAL RESEARCH

Contract N00014-81-K-0611

Task No. NR 056-773

TECHNICAL REPORT NO. 6

A SOLUBLE LINEAR SCHIFF-BASE COORDINATION POLYMER

CONTAINING EIGHT-COORDINATE ZIRCONIUM(IV)

by

Ronald D. Archer, Marvin L. Illingsworth,

Denise N. Rau and Christopher J. Hardiman

Prepared for Publication

in

Macromolecules

University of Massachusetts

Department of Chemistry

Amherst, MA   01003

February 1985

Accession For

NTIS CRA&I X
DTIC TAB ☐
Unannounced ☐
Justification

By
Distribution/
Availability Codes

Dist | Avail and/or Special

A-1

DTIC COPY INSPECTED

1

A Soluble Linear Schiff-base Coordination Polymer Containing
Eight-coordinate Zirconium(IV)

RONALD D. ARCHER,* MARVIN L. ILLINGSWORTH,

DENISE N. RAU and CHRISTOPHER J. HARDIMAN

Department of Chemistry, University of Massachusetts, Amherst, MA 01003

ABSTRACT

The first soluble linear Schiff-base heavy metal coordination polymer has
been synthesized via the condensation of 1,2,4,5-tetraaminobenzene and
tetrakis(salicylaldehydato)zirconium(IV) in dry dimethyl sulfoxide. The
N,N',N",N"'-tetrasalicylidene-1,2,4,5-tetraaminobenzeneatozirconium(IV)
polymer has a number average molecular weight of up to 4.9×10^4 based on
inherent viscosity, gel permeation chromatography, and elemental analysis.
Spectral properties of this polymer indicate a structure analogous to the
model compound, bis(N,N'-disalicylidene-1,2-phenylenediamino)zirconium(IV).
Thermal characterization of the polymer is also discussed.

INTRODUCTION

Linear metal chelate polymers with Schiff-base ligands in which the
metal is a part of the polymer backbone[1-5] or is added to a polymeric
Schiff-base[5-10] are typically insoluble materials. The x-ray study of
bis(N,N'-disalicylidene-1,2-phenylenediamino)zirconium(IV)[11] shows that two
quadridentate Schiff-base ligands on zirconium(IV) are oriented such that a
polymeric extension should be distorted from a strictly linear geometry which
might cause intermolecular stacking and intractability, a serious problem in

2

the attempted polymerizations of divalent ions with Schiff-base (and other) bridging ligands.[12] Furthermore, the possibility of flexibility for nonrigid metal centers, even with conjugated organic bridging ligands, provided further incentive to use zirconium as the metal for synthesizing a tractable Schiff-base chelate polymer. Zirconium(IV) eight-coordinate chelates are typically nonrigid.[13] The D_{2d} dodecahedron and the D_{4d} square antiprism, which are the two most common geometrical arrangements for eight ligand donor atoms around a central metal ion, are very similar in energy and normally possess a low energy barrier to interconversion; thus, nonrigid behavior is typical, even for chelates.

Zirconium(IV) is a labile metal ion; therefore, we have used a bis(quadridentate) delocalized chelating ligand, N,N',N",N"'-tetrasalicyli-dene-1,2,4,5-tetraaminobenzene, H_4tsb, 1, to retard the rate of ligand exchange in solution, to allow extensive polymer chain growth, and to provide good thermal stability.[14] Such Schiff-base ligands are capable of sufficient nonplanarity for the interconversion between the dodecahedron and the antiprism.[15,16] Thus, nonrigidity, suggested above, should still be possible.

$1, tsb^{4-}$

$2, dsp^{2-}$

The soluble red coordination polymer has been obtained through the condensation of tetrakis(salicylaldehydato)zirconium(IV), Zr(sal)$_4$, with 1,2,4,5-tetraaminobenzene, TAB, analogous to the reaction between Zr(sal)$_4$ and o-phenylenediamine, which we reported previously.[17] The low solubility of H$_4$tsb in ordinary solvents[18] caused us to investigate this alternative to polymerization through normal ligand displacement reactions. This ligand-forming condensation reaction (1) proved successful.[19]

$$[Zr(tsb)]_n \tag{1}$$

EXPERIMENTAL

Reagents

Reagent grade or equivalent solvents and chemicals were used. Prior to
use, dimethyl sulfoxide (DMSO), γ-collidine, N-methylpyrrolidone (NMP), and
mesitylene over calcium hydride were distilled under reduced pressure;
methylene chloride over calcium hydride, and methanol and acetone over
anhydrous calcium sulfate, were distilled at atmospheric pressure. A nitrogen
atmosphere was used in the presence of free amines, with $Zr(sal)_4$, and during
the polymerization reactions.

Tetrakis(salicylaldehydato)zirconium(IV)

$Zr(sal)_4$ was prepared as previously described[17] and used promptly.

Poly[N,N',N'',N'''-tetrasalicylidene-1,2,4,5-tetraaminobenzeneatozirconium(IV)]

1,2,4,5-Tetraaminobenzene(TAB) tetrahydrochloride (Burdic and Jackson
Laboratories) was dehydrohalogenated prior to use modifying the method of
Dudgeon.[20] Twenty-five mL of oxygen-free water, 5.0 g (0.017 mol) TAB·4HCl and
a small amount of Norit A were mixed and heated to boiling under a nitrogen
atmosphere. The hot mixture was suction-filtered into a dry-ice/acetone
chilled flask. The clear and nearly colorless filtrate was then quickly
transferred with stirring into 25 mL of ice-cold 15% aqueous NaOH solution and
the free TAB instantly precipitated as white flakes. The mixture was
filtered, ice-water washed, dried _in vacuo_, and weighed under nitrogen; yield,
1.43 g, 58%.

Then 0.816 g (5.92 mmol) TAB and 3.401 g (5.92 mmol) freshly prepared $Zr(sal)_4$ were separately dissolved in 100 mL and 200 mL, respectively, of dry, deoxygenated DMSO under a nitrogen atmosphere. The pale tan tetraamine solution was added in one portion to the chartreuse-yellow $Zr(sal)_4$ solution in a 500-mL flask. A deep red color developed immediately. With continued magnetic stirring, the DMSO-water azeotrope was slowly distilled under reduced pressure (41°, 1.6 torr), leaving a red glassy solid, which was purified by dissolution in dry DMSO and precipitated with dry acetone.

<u>Anal</u>. Calcd. for $[C_{34}H_{22}N_4O_4Zr]_n$: C, 63.6; H, 3.43; N. 8.73; Zr, 14.2. Calcd. for 0.1 mol DMSO/Zr(tsb): C, 63.2; H, 3.5; N, 8.6; S, 0.5; Zr, 14.0. Found:[21] C, 62.7; H, 3.8; N, 8.3; S, 0.8; Zr, 14.1.

Analysis of a sample prepared by <u>in vacuo</u> removal of DMSO solvent without the addition of acetone indicates about 1.7 moles DMSO per Zr unit and a Zr:4N ratio of 1.018. Calcd. for $Zr_{31}(C_{34}H_{22}N_4O_4]_{30}(OH)_4 \cdot 53C_2H_6SO$: C, 57.4; H, 4.2; N, 7.1; S, 7.2; Zr, 12.0. Found: C, 57.1; H, 4.3; N, 7.0; S, 6.9; Zr, 11.6.

Bis(quadridentate) Schiff-base Ligands

Free TAB (1.20 g, 8.1 mmol) prepared as above was dissolved in 175 mL of dried deoxygenated DMSO, and a stoichiometric amount (3.95 g, 32.4 mmol) of salicylaldehyde was added. The resulting deep red solution was allowed to stand overnight under nitrogen. The copious red-orange precipitate which formed was filtered under a nitrogen stream, washed several times with dried acetone, and dried <u>in vacuo</u>.

<u>Anal</u>. Calcd. for $C_{34}H_{26}N_4O_4$: C, 73.6; H, 4.69; N, 10.1. Found: C,72.7; H, 4.71; N, 9.7. Less than 0.15 mol DMSO gives excellent analytical agreement.

Derivatives of H_4tsb were prepared from the reaction of substituted salicylaldehydes with TAB using an excess of the aldehyde as a melt-solvent. For example, 0.8 g (6 mmol) of TAB and 20. g (130 mmol) of 3-methoxysalicylaldehyde were allowed to react for 20 min. at 50^o Hot filtration of the excess molten aldehyde from the fine red precipitate was followed by trituration with methanol and ethyl ether to remove any final traces of the aldehyde. The precipitate was dried in vacuo at room temperature for 24 hr; yield, 1.8 g, 50%; mp. $261-2^o$ (dec).

Anal. Calcd. for $C_{38}H_{34}N_4O_8$: C, 67.7; H, 5.04; N, 8.31. Found: C, 67.8; H, 4.99; N, 8.21.

Similarly, an analogous reaction between 1.0 g (7.2 mmol) of TAB and 20. g of molten 5-methoxysalicylaldehyde yielded 3.5 g, 70%, of a product with a mp., $280-280.5^o$ (dec).

Anal. Calcd. for $C_{38}H_{34}N_4O_8$: C, 67.7; H, 5.04; N, 8.31. Found: C, 68.0; H, 5.19; N, 8.17.

Condensation of TAB with excess 5-bromosalicylaldehyde and 2-hydroxy-1-naphthaldehyde gave products of very low solubility in common organic solvents. They were not purified.

Physical Properties

The same instrumentation and physical methods of characterization cited previously[17] were employed. In addition, thermal changes of polymer and model compounds were determined using a Dupont 900 Thermal Analyzer with a gas (nitrogen or air) flow of 0.2 liters per minute, a heating rate of 10^o per minute, a sample size of 10 milligrams, and measured against aluminum chloride as a reference. Sample weight losses corresponding to these thermal changes

were measured on a Dupont 950 Thermogravimetric Analyzer using samples of similar size under identical conditions. Preliminary thermal decomposition pyrolysis was accomplished with a Chromalytics MP-3 Multi-purpose Thermal Analyzer. The products were trapped on glass beads using liquid nitrogen and separated with a Varian Aerograph Series 2700 gas chromatograph using Chromasorb 102 for the low boiling components and General Electric S.E. 30 on Chromasorb W support for the high boiling components.

Viscosity data in triplicate were collected in a Canon-Fenske Model No. 100-2873 viscometer or in an Ubbelohde Model No. 1, 2568 viscometer, equilibrated at $30.00 \pm 0.02^{\circ}$. The solvent was NMP.

A weight-loss experiment was conducted with a "furnace" consisting of a 6" test tube in a Wood's metal bath. A smaller 4" test tube served as the sample container. The sample container was preconditioned in the furnace for 24 hrs. prior to removal for rapid weighing, addition of 0.1 g polymer, reweighing, reheating, reweighing, etc. Weighings were to $\pm$ 0.2 mg.

Gel permeation chromatography of the zirconium polymer was conducted on a 10^3 Angstrom Ultrastyragel column (Waters) with N-methyl-2-pyrrolidone (NMP) as the solvent.

RESULTS

Whereas H_4tsb and its derivatives have very limited solubility, the reaction between $Zr(sal)_4$ and TAB in DMSO produces an oligomer which is orders of magnitude more soluble. Solvent removal in vacuo or the addition of a miscible nonsolvent such as acetone is necessary to isolate a solid product.

Because the isopropyl derivative of H_4tsb had shown improved solubility over the unsubstituted compound,[22] several derivatives were prepared to improve the solubility over the parent ligand while avoiding carbon–carbon single bonds. In dry donor solvents such as DMSO and γ-collidine, the 3- and 5-methoxy derivatives, which are reported here, show only modest solubility improvement relative to the parent compounds, while the slightly impure Schiff-base products obtained from condensation of 5-bromosalicylaldehyde or 2-hydroxy-1-naphthaldehyde with TAB show no solubility improvement at all.

These modest improvements are in sharp contrast to the polymer solubility improvement obtained in the chelate preparation between $Zr(sal)_4$ and TAB in DMSO. The soluble polymer solutions produce thin, light-diffracting films upon the slow evaporation of the DMSO solvent. [DMSO solutions of the free H_4tsb ligand produce crystalline particles.] The red glassy polymer appears to be amorphous since no x-ray diffraction pattern could be obtained, and under microscopic examination the polymer appears as red translucent irregular shaped particles with black striae.

The underline{elemental analyses} indicate 0.1 to 1.7 DMSO molecules per zirconium unit, the quantity of DMSO is dependant on the solvent mix. After considering the DMSO solvation, the excess of oxygen (by difference) is suggestive of OH end groups and/or water in the DMSO reaction product. Elemental analyses for N and Zr for a variety of samples indicate 1 ligand to 1 Zr within experimental error.

underline{Inherent viscosities} for $Zr(dsp)_2$ and the glassy $Zr(tsb)$ polymer samples were determined using Kraemer's approximation:[23]

$$[\eta]_{inh} = (1/c) \ln (T_{solution}/T_{solvent})$$

9

where $[\eta]_{inh}$ = inherent viscosity

  c = concentrations in g/dL

  T = time in seconds

Samples of the polymer have been prepared which have inherent viscosity values

of up to 0.18 dL/g in NMP as noted in Table I. The inherent viscosities of

the polymer samples show negligible concentration dependence for series of

dilute solutions so extrapolation to intrinsic viscocities is straight forward.

Gel permeation chromatography of the Zr(tsb) polymer samples in NMP

yield number average molecular weights of as much as 49,000 relative to

polystyrene standards as noted in Table I. The data for monomeric $Zr(dsp)_2$ is

also included in Table I.

Comparing the Zr(tsb) polymer with the free ligand, the infrared

frequency shifts are analogous to those observed for $Zr(dsp)_2$ relative to

H_2dsp except for the persistence of O-H vibrations in the polymer. See Table

II. The phenyl ring to oxygen stretch is shifted by 35 cm^{-1} to higher

frequencies in both the model chelate and the polymer relative to the

respective neutral ligands. The imine C=N stretching vibration, by contrast,

is almost unaffected, with frequency decreases of only a few wave numbers in

both cases. The major difference is in the O-H stretching region, which shows

no absorption in the model chelate, but persists with a peak and a shoulder in

the polymer.[24]

The zirconium polymer has an electronic spectrum in DMSO which is more

complex and has lower energy transitions than those of the free ligand in the

same solvent. Very similar behavior has been noted in the model $Zr(dsp)_2$

system,[11] and in other transition metal complexes of this ligand.[18,22] See

Table III.

10

Unlike monomeric $Zr(dsp)_2$ which has well behaved mass spectra[11] the polymer is not sufficiently volatile even at 275° to give a meaningful mass spectrum. Only a few very minor peaks are observed at mass to charge ratios of less than 300 m/e.

Thermal analysis of the polymer and the model compound by differential thermal analysis (DTA), thermogravimetric analysis (TGA), and pyrolysis-gas chromatography(P-GC) shows many analogous features as anticipated for compounds of similar structure. The DTA of the $[Zr(tsb)]_n$ polymer has a small endotherm which appears in the $130^{\circ}-190^{\circ}$ range, probably due to loss of water and DMSO,[25] and thus is not observed in the DTA of the model compound. A noticeable weight loss near 160° is apparent in the polymer's TGA but not in the TGA of $Zr(dsp)_2$, which is consistent with this interpretation.

The next feature, ascending in temperature, is a small exotherm which occurs at $225-250^{\circ}$ for the polymeric species in either nitrogen or air. While the DTA of freshly recrystallized, vacuum dried $Zr(dsp)_2$ is featureless at these temperatures, samples that have been allowed to stand at length in air display a nearly identical exotherm to the one described above in either nitrogen or air. In the TGA of one nine-month-old sample of $Zr(dsp)_2$, a corresponding two percent weight loss was observed; the analogous feature in the polymer TGA is masked by the DMSO evaporation.

In order to discern if a slow decomposition reaction occurs at room temperature or if a bond breaking and bond forming reaction takes place upon heating, infrared spectra of the fresh, aged, and heated (to 270°) $Zr(dsp)_2$ samples were recorded. The only difference displayed by the aged samples in comparison to the previously reported infrared spectrum of purified $Zr(dsp)_2$[11]

CAPTION FOR FIGURE

Figure.--The anticipated structure for a portion of the $[Zr(tsb)]_n$ polymer. The larger circles represent the Zr atoms and neither the ring below the plane of the molecule nor the H atoms are shown. The dodecahedral coordination about Zr is shown in Inset A. Note that organic portion of the ligand perpendicular to the plane of Inset A is skewed (cf., ref. 11) and provides two confirmation possibilities, the trans one shown for the chain and the cis one shown in Inset B, where the arrow points to the two nitrogens (one is below the one shown) with the changed configuration. Molecular models show that the configuration is possible, but the steric interactions cause us to favor the trans configuration shown at the left.

TABLE III. Electronic Spectral Results, cm^{-1} {log ε}[a]

$[Zr(tsb)\cdot1.7\ DMSO]_n$	$H_4(tsb)$	$H_4[(3\text{-methoxy})_4tsb]$	$H_4[(5\text{-methoxy})tsb]$
39,000 sh[b]	36,700 {4.40}[c]	34,600 {4.45}	35,500 {4.36}
30,800 {4.45}	29,800 sh[d]	29,200 sh	30,300 sh
	28,300 {4.55}[c]	27,900 {4.62}	27,000 {4.57}
26,500 w,sh	25,600 {4.50}[c]	26,500 {4.61}	25,600 {4.61}
24,200 w,sh			
22,400 {4.59}	23,900 sh[d]	24,400 sh	23,500 sh
21,200 sh			

[a]one cm matched cells, DMSO as solvent; [b]CH_2Cl_2 as solvent; [c]Ref.18; [d]This work.

24

TABLE II. Infrared Spectral Results for the New Compounds [Zr(tsb)]$_n$ Polymer, H$_4$(3-methoxy)$_4$tsb, and H$_4$(t-methoxy)$_4$tsb, cm^{-1} [a]

Assignment	[Zr(tsb)]·1.7 DMSO]$_n$	H$_4$(tsb)	H$_4$[(3-methoxy)$_4$tsb]	H$_4$[(5-methoxy)$_4$tsb]
(O-H)ν terminal[c]	3650 sh[c]			
(O-H)ν H-bonded or bridging	3430 br[c]	3500 w, br	3450 br	3450 br
(C=N)ν	1602 s[c]	1610 s	1612 / 1605 } s	1622 m ; 1337 m[d]
M-(O-ϕ)ν	1310 m[c]			
H(O-ϕ)ν, H$_3$C(O-ϕ)ν [b]		1275 ms	1268 sh ; 1250 s	1270 s ; 1252 m
H$_3$(C-O)ν [b]			1228 w, sh	1228 w
DMSO (S-O)ν	1025 br			

[a]KBr pellets; [b]tentative assignments; [c]abbreviations; [d]unknown assignment. abbreviations: ν = stretching mode, sh = shoulder, br = broad, s = strong, m = medium, w = weak; unknown assignment.

TABLE I. GPC and Viscosity Data for Polymeric Zr(tsb) in NMP.

Volume[a]	$\bar{M}_n$(PS)[b]	$[\eta]$[c]	$\bar{M}_\eta$[d]
5.65	49,000	0.177±0.015	104,000±9,000
5.89	38,000	0.140±0.009	87,000±7,000
6.17	28,000	0.117±0.018	64,000±10,000
6.24	26,000	0.091±0.008	72,000±7,000
9.54	760[e]	0.02 ±0.01	1,000± 500

[a]Retention volume in mL on a 10^3 Angstrom Ultrastyragel GPC column with NMP as the solvent. [b]Polystyrene equivalent number average molecular weight based on calibration with eleven standards. [c]Intrinsic viscosity in NMP at 30.0°C in dL/g. [d]Molecular weight based on viscocity/GPC universal calibration curve method. [e]Model monomeric zirconium Schiff-base chelate with a molecular weight of 690.

32. Carraher, C.E.,Jr.; Sheats, J.E.; Pittman, C.U.,Jr. "Organometallic Polymers." Academic Press, New York, 1978, pp. 1, 13, 25, 39, 53, 67, 87, 107, and 181.

33. Illingsworth, M.L.; Archer, R.D. Polyhedron, 1982, 1, 487.

16. Hill, W.E.; Atabay, N.; McAuliffe, C.A.; McCullough, F.P.; Razzoki, S.M. Inorg. Chim. Acta, 1979, 35, 35.

17. Archer, R.D.; Illingsworth, M.L. Inorg. Nucl. Chem. Lett., 1977, 13, 661.

18. Merrell, P.H.; Osgood, R.A. Inorg. Chim. Acta, 1975, 14, L33.

19. Archer, R.D.; Batschelet, W.H.; Illingsworth, M.L. J. Macromol. Sci. - Chem., 1981, A16, 261 gives a preliminary report on the polymer-based on a paper presented at an Am. Chem. Soc. Symposium; in part from Illingsworth, M. L., Ph. D. Dissertation, Univ. of Massachusetts, 1980.

20. Dudgeon, C.D., Ph.D. Dissertation, University of Massachusetts, Amherst, 1976.

21. Analyses by University of Massachusetts Microanalytical Laboratory.

22. Merrell, P.H.; Maheu, L.J. Inorg. Chim. Acta, 1978, 28, 47.

23. Kraemer, E.O. Ind. Eng. Chem., 1938, 30, 1200.

24. Carraher, C.E.,Jr; Sheats, J.E.; Pittman, C.U.,Jr. "Organometallic Polymers", Academic Press, New York, 1978, p. 90.

25. Reynolds, W.L. Progr. Inorg. Chem., 1970, 12, 1.

26. Conciatori, A.B.; Chenevey, E.C.; Bohrer, T.C.; Prince, A.E.,Jr. J. Polym. Sci., C, 1967, 5, 49.

27. Syromiatrikov, W.; Prot, T. Polimery, (Warsaw), 1977, 22, 365; Chem. abstr., 1978, 89, 75485h.

28. Fuchs, O.; Suhr, H.H. "Polymer Handbook," 2nd Ed., Wiley, New York, 1975, p. iv-241.

29. Pittman, C.U. Jr.; Hirao, A. J. Polym. Sci. - Polym. Chem. Ed., 1977, 15, 1677. A viscosity of 0.140 corresponded to a M_n of 40,600.

30. Rodriguez, F. "Principles of Polymer Systems", McGraw-Hill, New York, 1970, p. 154.

31. Gillman, H.D.; Nannelli, P. Inorg. Chem. Acta, 1977, 23, 259.

REFERENCES AND FOOTNOTES

1. Karampurwala, A.M.; Patel, R.P.; Shah, J.R. <u>Angew. Makromol. Chem.</u>, 1980, <u>89</u>, 57; <u>ibid.</u>, <u>87</u>, 87.

2. Karampurwala, A.M.; Patel, R.P.; Shah, J.R. <u>J. Macromol. Sci.-Chem.</u>, 1981, <u>A15</u>, 431 and 439.

3. Patil, M.S.; Shah, N.R.; Rama, A.K.; Karampurwala, A.M.; Shah, J.R. <u>J. Macromol. Sci.-Chem.</u>, 1981, <u>A16</u>, 737.

4. Deshpande, U.G.; Shah, J.R. <u>J. Macromol. Sci.-Chem.</u>, 1983, <u>A20</u>, 355.

5. Trent'ev, A.R.; Rode, V.V.; Nekrasov, L.I.; Rukhadze, E.G. <u>Vysokomol. Soedin.</u>,1960, <u>2</u>, 1557; <u>ibid.</u>, 1962, <u>4</u>,13.

6. Marvel, C.S.; Tarkoy, N.T. <u>J. Am. Chem. Soc.</u>, 1957, <u>79</u>, 6000; <u>ibid.</u>, 1958, <u>80</u>, 832.

7. Goodwin, H.A.; Bailar, J.C.,Jr. <u>J. Am. Chem. Soc.</u>, 1961, <u>83</u>, 2467.

8. Manecke, G.; Wille, W.E. <u>Makromol. Chem.</u>, 1970, <u>133</u>, 61.

9. Sawodny, W.; Gruenes, R.; Reitzle, H. <u>Angew. Chem.</u>, 1982, <u>94</u>, 803; <u>Angew. Chem.</u> Suppl., 1982, 1662; and references cited therein.

10. Bottino, F.A.; Finocchiaro, P.; Libertini, E.; Mamo, A.; Recca, A. <u>Polymer Commun.</u>, 1983, <u>24</u>, 63.

11. Archer, R.D.; Day, R.O.; Illingsworth, M.L. <u>Inorg. Chem.</u>, 1979, <u>18</u>, 2908.

12. Sheats, J.E. <u>Kirk-Othmer Ency. Chem. Tech.</u>, 3rd. ed., 1981, <u>15</u>, 184.

13. Fay, R.C.; Howie, J.K. <u>J. Am. Chem. Soc.</u>, 1979, <u>101</u>, 115, and references cited therein.

14. Carraher, C.E., Jr. <u>J. Macromol. Sci.-Chem.</u>, 1982, <u>A17</u>, 1293; and references cited therein.

15. Cummins, D.; McKenzie, E.D.; Milburn, H. <u>J. Chem. Soc., Dalton Trans.</u>, 1976, 130.

either alone or as composites. Our aim is to obtain species with improved solubility, flexibility, high thermal stability, and extended conjugation.

ACKNOWLEDGMENT

polymers have shown thermal stabilities in excess at 300°.[14]

The close similarities between the polymer spectra and thermal data with those of the model system suggest that the chelation in the Zr(tsb) units is analogous to that observed by x-ray diffraction for $Zr(dsp)_2$.[11] Thus, if the chelating part of the tsb^{4-} ligand is as flexible as the corresponding dsp^{2-} ligand,[11,15,16] then some degree of nonrigidity is possible in the polymer.

Condensation polymerizations using the water scavenger, 2,2'-dimethoxypropane, DMP,[31] were attempted, but no perceivable increases in the average polymer chain length were obtained. Thus, we conclude that either DMP does not diminish the rate of chain termination, or that imprecise stoichiometry limited the chain growth.

Coordination polymerization of pre-made ligands with reactive zirconium starting materials was also investigated. Stoichiometric (1:2) model reactions between either zirconium tetra-alkoxides or tetrakis-(acetylacetonato)zirconium(IV) and a quadridentate Schiff-base ligand did not produce clean products in high enough yields to warrant any further attempts at analogous polymerization reactions, although this method has met with some success in the past.[12] Solubility problems limit polymer growth in this system by this method.

In light of the tetrakis(salicylaldehydato)zirconium(IV) chelate hydrolysis and the bis(quadridentate) ligand insolubility, ligand-centered polymerization[32] reactions of preformed eight-coordinate chelates have been considered. The hydrolytic stability of $Zr(dsp)_2$ which can be recrystallized from ordinary reagent-grade benzene and petroleum ether without decomposition, is encouraging in this regard. We have initiated studies in this area[33] as we attempt to make long fibers of coordination polymers having unique properties, either alone or as composites. Our aim is to obtain species with improved

recrystallized $Zr(dsp)_2$ necessarily means that samples of the model compound undergo a very slow change upon standing in air at room temperature, but since acquisition of an O-H stretching mode at 3350-3600 cm^{-1} is the only change noted in the infrared absorbance spectrum, physical absorption of atmospheric water must be the only process occurring. Only upon heating to 240^o does a chemical reaction apparently take place between the absorbed water and the Schiff-base complex. New peaks in the infrared at 1627, 1163, and 763 cm^{-1} after heating are consistent with this interpretation. Tentative assignments as a C=O stretch, a 1,2-disubstituted in-plane C-H bend, and a 1,2-disubstituted out-of-plane C-H bend, respectively, are consistent with a product resulting from hydrolysis of one imine bond.

Water produced during Schiff-base condensation presumably accounts for the analogous behavior of the polymer. The broad hydrogen bonded O-H stretch in the infrared spectrum of the polymer is consistent with water being present in addition to hydroxy end groups.[24] While the corresponding polymer weight loss also appears small in the TGA, extended heating in air at temperatures approximating this exothermic feature produces a much more substantial weight loss, up to 46% after one week; accordingly, this could be due to an on-going reaction with atmospheric moisture, or secondary reactions of hydrolyzed products. Several other Schiff-base polymers, Schiff-base coordination polymers and chelates show weight loss very near this temperature range.[14]

It should be pointed out that with quadridentate ligands other than Schiff-bases, zirconium coordination polymers might not show this feature. In the absence of this hydrolysis exotherm, the only other feature is a major decomposition due to combustion in air, TGA weight loss at 370^o, with no decomposition occurring in nitrogen up to 500^o. Other zirconium containing

The inherent viscosity values of up to about 0.18 dL/g for the polymer samples in NMP indicates a reasonable degree of polymerization, especially when coupled with the GPC results. The second order viscosity term in Kraemer's equation is unnecessary. A Universal Calibration treatment of the data provide an estimate of higher molecular weights as suggested above. The only reference point is the model monomer, which provides an indication that the retention volumes and viscosities are as anticipated. Attempts to estimate the molecular weight from the viscosity with the Mark-Houwink equation[30]

$$[\eta] = KM^a \tag{3}$$

are difficult because no soluble coordination polymers similar to Zr(tsb) exist for which K and a values have been determined. Attempts to measure the absolute molecular weights directly have been frought with insurmountable problems. The fluorescence of the polymer has precluded precise results through light scattering and attempts to use membrane osmometry have been thwarted by the instability of the membranes in NMP. Thus, we are stuck with the "ball park" figures of between 49,000 based on the direct GPC measurements relative to polystyrene and the 100,000 value from the Universal Calibration curve, again relative to polystyrene. We have chosen the more conservative number for our claims.

Since the endothermic loss of DMSO from the polymer represents desolvation, the 225-250° exotherm in the polymer DTA, and similarly for aged samples of Zr(dsp)$_2$, represents the first bond-breaking and bond-forming chemical reaction. The observation that this feature does not occur in freshly

15

separately dissolved in DMSO so that the dissolution rate would not be the rate determining step in the polymerization reaction. Formation of the deep-red color associated with the polymeric product begins almost instantaneously upon mixing of the solutions at room temperature.

The formation of light-diffracting films upon evaporation of the solvent is a property often shown by, but not limited to, soluble polymers. More concrete evidence is deduced from the GPC, viscosity and analysis results.

The GPC results of up to 49,000 ($\overline{M}_n$) indicate an average degree of polymerization ($\overline{DP}$) of up to about 80. The results could be underestimating the molecular weight, since the monomeric unit is 643 Daltons, and molecular weight models suggest each monomeric unit is about twice the size of a polystyrene unit. Thus an appreciably higher molecular weight is possible. On the other hand, the large orientation angle between ligands estimated from the x-ray study[11] might give a pseudo rigid-rod effect. Unfortunately no other heavy metal chelate polymers are available for comparison. Ferrocene polymers, the closest type, do appear to give results similar to organic polymers.[29]

Consideration of the zirconium:ligand ratio of 1.018 and the elemental analysis corrected for the solvated DMSO suggests an average chain length of 20 to 50 units even if all of the end groups were hydroxides for the lowest molecular weight sample polymer in Table I. Given the equal probability of ligand end groups and of water to be coordinated along the chain or at the ends of the chains, the true degree of polymerization could be appreciably higher. The other samples have ligand to zirconium ratios of one to one within experimental error. Naturally, the effect of end groups on the elemental percentages becomes minimal, i.e. within analytical error, when large degrees of polymerization have been attained.

14

DISCUSSION

The dramatic difference in the solubility of the Zr(tsb) polymer relative to the free ligand[18] or its derivatives[22] or most other coordination polymers[12] is potentially very significant. Industrially, polymer solubility is very important; e.g., concentrated DMSO solutions called dopes are used for spinning certain polymer fibers.[26] Characterization is also more definitive for soluble species. One feature which may in part be responsible for this solubility difference is the puckered, perpendicularly arranged, quadridentate ligands anticipated from the model compound x-ray structure,[11] in which the ligands show no tendency to stack with either benzene solvate molecules or chelate ligands from adjacent molecules. Models of the polymer chains, assuming the described stereochemistry, also depict steric reasons for significantly reduced lattice forces (cf., the Figure). Nonrigid molecular motion may further hinder packing of the polymer chains. However, average chain length must also be considered as a major factor in comparing solubilities with other coordination polymers. Other ligand-forming polymerizations which allow extended chain lengths are rare.[8]

The Schiff-base polymerization reaction is known to be a high yield reaction both with and without transition metals.[6-10,27] Also, the method used herein avoids the solubility problem associated with premade H_4tsb ligands. However, the production of water in the presence of hydrolytically reactive Zr(sal)$_4$[17] is of particular concern. Thus, DMSO, which is known for its strong hydrogen-bonding with water[25] and its properties as a polymer solvent,[26,28] was chosen as the reaction medium. Both reactants were

is the presence of a broad absorption at 3350-3600 cm^{-1} due to an O-H stretching mode. The heated sample, however, not only maintains an O-H stretching mode, but three new absorptions at 1627, 1163, and 763(sh) cm^{-1} indicate that a new organic species is present.

The final thermal gravimetric feature displayed by both zirconium species is a large weight loss due to burning in air. This process begins at a slightly lower temperature for the polymer (380°) than for the model compound (400°). This chemical change is corroborated by the DTA: In air, the huge corresponding exotherm actually begins at less than 300° for the polymer, and at about 400° for $Zr(dsp)_2$. However, a rather dramatic difference occurs under nitrogen: whereas the anerobic decomposition of the model compound is almost coincident to its combustion temperature, the polymer shows no such decomposition at temperatures below 500°.

Pyrolysis-gas chromatographic results, by contrast, are of greatest value as a fingerprint method. As anticipated for compounds of similar chemical structure, the gas chromatograms are consistent with the production of several identical pyrolysis fragments in the polymer and the model monomer. Extended heating of polymer samples in air at temperatures approximating the small exotherm (240°C) produces considerably larger weight losses than those observed at this temperature during slow TGA scans. Approximately 22% and 46% weight losses were observed after 1 and 7 days, respectively, for the 1.7 DMSO solvate polymer. These weight losses are comparable to previous weight loss results for other metal-chelate Schiff-base polymers.[6-10,14]

12

A

B

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	No. Copies		No. Copies
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. Vincent Schaper DTNSRDC Code 2830 Annapolis, Maryland 21402	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. G. A. Somorjai
Department of Chemistry
University of California
Berkeley, California 94720

Dr. W. Kohn
Department of Physics
University of California, San Diego
La Jolia, California 92037

Dr. J. Murday
Naval Research Laboratory
Surface Chemistry Division (6170)
455 Overlook Avenue, S.W.
Washington, D.C. 20375

Dr. R. L. Park
Director, Center of Materials
  Research
University of Maryland
College Park, Maryland 20742

Dr. J. B. Hudson
Materials Division
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. W. T. Peria
Electrical Engineering Department
University of Minnesota
Minneapolis, Minnesota 55455

Dr. Theodore E. Madey
Surface Chemistry Section
Department of Commerce
National Bureau of Standards
Washington, D.C. 20234

Dr. Keith H. Johnson
Department of Metallurgy and
  Materials Science
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. Chia-wei Woo
Department of Physics
Northwestern University
Evanston, Illinois 60201

Dr. J. M. White
Department of Chemistry
University of Texas
Austin, Texas 78712

Dr. Robert M. Hexter
Department of Chemistry
University of Minnesota
Minneapolis, Minnesota

Dr. R. P. Van Duyne
Chemistry Department
Northwestern University
Evanston, Illinois 60201

Dr. J. E. Demuth
IBM Corporation
Thomas J. Watson Research Center
P.O. Box 218
Yorktown Heights, New York 10598

Dr. S. Sibener
Department of Chemistry
James Franck Institute
5640 Ellis Avenue
Chicago, Illinois 60637

Dr. M. G. Lagally
Department of Metallurgical
  and Mining Engineering
University of Wisconsin
Madison, Wisconsin 53706

Dr. Arold Green
Quantum Surface Dynamics Branch
Code 3817
Naval Weapons Center
China Lake, California 93555

Dr. Adolph B. Amster
Chemistry Division
Naval Weapons Center
China Lake, California 93555

Dr. S. L. Bernasek
Princeton University
Department of Chemistry
Princeton, New Jersey 08544

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. F. Carter
Code 6132
Naval Research Laboratory
Washington, D.C. 20375

Dr. Richard Colton
Code 6112
Naval Research Laboratory
Washington, D.C. 20375

Dr. Dan Pierce
National Bureau of Standards
Optical Physics Division
Washington, D.C. 20234

Professor R. Stanley Williams
Department of Chemistry
University of California
Los Angeles, California 90024

Dr. R. P. Messmer
Materials Characterization Lab.
General Electric Company
Schenectady, New York 22217

Dr. Robert Gomer
Department of Chemistry
James Franck Institute
5640 Ellis Avenue
Chicago, Illinois 60637

Dr. Ronald Lee
R301
Naval Surface Weapons Center
White Oak
Silver Spring, Maryland 20910

Dr. Paul Schoen
Code 5570
Naval Research Laboratory
Washington, D.C. 20375

Dr. John T. Yates
Department of Chemistry
University of Pittsburgh
Pittsburgh, Pennsylvania 15260

Dr. Richard Greene
Code 5230
Naval Research Laboratory
Washington, D.C. 20375

Dr. L. Kesmodel
Department of Physics
Indiana University
Bloomington, Indiana 47403

Dr. K. C. Janda
California Institute of Technology
Division of Chemistry and Chemical
  Engineering
Pasadena, California 91125

Professor E. A. Irene
Department of Chemistry
University of North Carolina
Chapel Hill, Northc Carolina 27514

Dr. Adam Heller
Bell Laboratories
Murray Hill, New Jersey 07974

Dr. Martin Fleischmann
Department of Chemistry
Southampton University
Southampton SO9 5NH
Hampshire, England

Dr. John W. Wilkins
Cornell University
Laboratory of Atomic and
  Solid State Physics
Ithaca, New York 14853

Dr. Richard Smardzewski
Code 6130
Naval Research Laboratory
Washington, D.C. 20375

Dr. H. Tachikawa
Chemistry Department
Jackson State University
Jackson, Mississippi 39217

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. R. G. Wallis
Department of Physics
University of California
Irvine, California 92664

Dr. R. W. Plummer
Department of Physics
University of Pennsylvania
Philadelphia, Pennsylvania 19104

Dr. D. Ramaker
Chemistry Department
George Washington University
Washington, D.C. 20052

Dr. E. Yeager
Department of Chemistry
Case Western Reserve University
Cleveland, Ohio 41106

Dr. P. Hansma
Physics Department
University of California
Santa Barbara, California 93106

Professor D. Hercules
University Pittsburgh
Chemistry Department
Pittsburgh, Pennsylvania 15260

Dr. J. C. Hemminger
Chemistry Department
University of California
Irvine, California 92717

Professor N. Winograd
Department of Chemistry
Pennsylvania State University
University Park, Pennsylvania 16802

Professor T. F. George
Chemistry Department
University of Rochester
Rochester, New York 14627

Dr. G. D. Stein
Mechanical Engineering Department
Northwestern University
Evanston, Illinois 60201

Dr. G. Rubloff
IBM
Thomas J. Watson Research Center
P.O. Box 218
Yorktown Heights, New York 10598

Professor A. Steckl
Department of Electrical and
  Systems Engineering
Rensselaer Polytechnic Institute
Troy, NewYork 12181

Professor Horia Metiu
Chemistry Department
University of California
Santa Barbara, California 93106

Professor G. H. Morrison
Department of Chemistry
Cornell University
Ithaca, New York 14853

Captain Lee Myers
AFOSR/NC
Bollig AFB .
Washington, D.C. 20332

Dr. David Squire
Army Research Office
P.O. Box 12211
Research Triangle Park, NC 27709

Professor Roald Hoffmann
Department of Chemistry
Cornell University
Ithaca, New York 14853

Dr. R. D. Archer
Chemistry Department
University of Massachusetts
Amherst, Massachusetts 01003

TECHNICAL REPORT DISTRIBUTION LIST, 056

Dr. J. E. Jensen
Hughes Research Laboratory
3011 Malibu Canyon Road
Malibu, California 90265

Dr. J. H. Weaver
Department of Chemical Engineering
and Materials Science
University of Minnesota
Minneapolis, Minnesota 55455

Dr. W. Knauer
Hughes Research Laboratory
3011 Malibu Canyon Road
Malibu, California 90265

Dr. C. B. Harris
Department of Chemistry
University of California
Berkeley, California 94720

END

FILMED

4-85

DTIC